

# HP 3D High Reusability PA 11

Ductile, lowest cost,<sup>1</sup> quality parts



## Produce strong, ductile,<sup>2</sup> functional parts

- Thermoplastic material delivering optimal mechanical properties.
- Renewable raw material from vegetable castor oil (reduced environmental impact).<sup>3</sup>
- Provides excellent chemical resistance<sup>4</sup> and enhanced elongation-at-break.<sup>2</sup>
- Impact resistance and ductility<sup>2</sup> for prostheses, insoles, sports goods, snap fits, living hinges, and more.

## Quality at the lowest cost per part<sup>1</sup>

- Achieve the lowest cost per part<sup>1</sup> and reduce your total cost of ownership.<sup>5</sup>
- Minimize waste—reuse surplus powder batch after batch and get functional parts, no throwing away anymore.<sup>6</sup>
- Get consistent performance while achieving 70% surplus powder reusability.<sup>7</sup>
- Optimize cost and part quality—cost-efficient material with industry-leading surplus powder reusability.<sup>5</sup>

## Engineered for HP Multi Jet Fusion technology

- Designed for production of functional and final parts across a variety of industries.
- Provides the best balance between performance and reusability.<sup>8</sup>
- Easy-to-process material enables high productivity, less waste, and lower cost.<sup>9</sup>
- Engineered to reliably produce final parts and functional prototypes with fine detail, dimensional accuracy.



For more information, please visit  
[hp.com/go/3DMaterials](https://hp.com/go/3DMaterials)

# Technical specifications<sup>10</sup>

Category	Measurement	Value	Method
General Properties	Powder melting point (DSC)	202 °C/396 °F	ASTM D3418
	Particle size	50 µm	ASTM D3451
	Bulk density of powder	0.48 g/cm <sup>3</sup>	ASTM D1895
	Density of parts	1.04 g/cm <sup>3</sup>	ASTM D792
Mechanical Properties	Tensile strength, max load <sup>11</sup> , XY	50 MPa/7250 psi	ASTM D638
	Tensile strength, max load <sup>11</sup> , Z	50 MPa/7250 psi	ASTM D638
	Tensile modulus <sup>11</sup> , XY	1800 MPa/261 ksi	ASTM D638
	Tensile modulus <sup>11</sup> , Z	1800 MPa/261 ksi	ASTM D638
	Elongation at break <sup>11</sup> , XYZ	50%	ASTM D638
	Flexural strength (@ 5%) <sup>12</sup> , XY	60 MPa/8700 psi	ASTM D790
	Flexural strength (@ 5%) <sup>12</sup> , Z	60 MPa/8700 psi	ASTM D790
	Flexural modulus <sup>12</sup> , XY	1600 MPa/232 ksi	ASTM D790
	Flexural modulus <sup>12</sup> , Z	1600 MPa/232 ksi	ASTM D790
Thermal Properties	Izod impact notched (@ 3.2 mm, 23 °C), XYZ	6 kJ/m <sup>2</sup>	ASTM D256 Test Method A
	Heat deflection temperature (@ 0.45 MPa, 66 psi), Z	183 °C/361 °F	ASTM D648 Test Method A
Thermal Properties	Heat deflection temperature (@ 1.82 MPa, 264 psi), Z	50 °C/122 °F	ASTM D648 Test Method A
	Recyclability	Refresh ratio for stable performance	30%

## Ordering Information

HP 3D High Reusability PA 11		
Product Number	V1R12A	V1R18A
Weight	14 kg	140 kg
Capacity	30L <sup>13</sup>	300L <sup>13</sup>
Dimensions (xyz)	600 x 333 x 302 mm	800 x 600 x 1205 mm
Compatibility	HP Jet Fusion 3D 4210/4200/3200 Printing Solution	HP Jet Fusion 3D 4210/4200 Printing Solution

### Eco Highlights

- Powders and agents are not classified as hazardous<sup>14</sup>
- Cleaner, more comfortable workplace—enclosed printing system, and automatic powder management<sup>15</sup>
- Minimizes waste due to industry-leading reusability of powder<sup>16</sup>

Find out more about HP sustainable solutions at [hp.com/go/ecosolutions](http://hp.com/go/ecosolutions)

Learn more at [hp.com/go/3DMaterials](http://hp.com/go/3DMaterials)

- Based on internal testing and public data, HP Jet Fusion 3D printing solution average printing cost per part is half the cost of comparable fused deposition modeling (FDM) and selective laser sintering (SLS) printer solutions from \$100,000 USD to \$300,000 USD, when averaged together and not taken individually, in market as of April 2016. Cost analysis based on: standard solution configuration price, supplies price, and maintenance costs recommended by the manufacturer. Cost criteria: printing 1-2 buckets per day/5 days per week over 1 year of 30-gram parts at 10% packing density using the powder reusability ratio recommended by the manufacturer.
- Testing according to ASTM D638, ASTM D256, and ASTM D648 using HDT at different loads with a 3D scanner for dimensional stability. Testing monitored using statistical process controls.
- HP 3D High Reusability PA 11 powder is made with 100% renewable carbon content derived from castor plants grown without GMOs in arid areas that do not compete with food crops. HP 3D High Reusability PA 11 is made using renewable sources, and may be made together with certain non-renewable sources. A renewable resource is a natural organic resource that can be renewed at the same speed in which it is consumed. Renewable stands for the number of carbon atoms in the chain coming from renewable sources (in this case, castor seeds) according to ASTM D6866.
- Tested with diluted alkalis, concentrated alkalis, chlorine salts, alcohol, ester, ethers, ketones, aliphatic hydrocarbons, unleaded petrol, motor oil, aromatic hydrocarbons, toluene, and DOT 3 brake fluid.
- Compared to selective laser sintering (SLS) and fused deposition modeling (FDM) technologies, HP Multi Jet Fusion technology can reduce the overall energy requirements needed to attain full fusing and reduce the system requirements for large, vacuum-sealed ovens. In addition, HP Multi Jet Fusion technology uses less heating power than SLS systems for better material properties and material reuse rates, minimizing waste.
- Based on using recommended packing densities and compared to selective laser sintering (SLS) technology, offers excellent reusability without sacrificing mechanical performance. Tested according to ASTM D638 and MFI test using HDT at different loads with a 3D scanner for dimensional stability. Testing monitored using statistical process controls. Liters refers to the materials container size and not the actual materials volume. Materials are measured in kilograms.
- HP Jet Fusion 3D printing solutions using HP 3D High Reusability PA 11 provide 70% post-production surplus powder reusability, producing functional parts batch after batch. For testing, material is aged in real printing conditions and powder is tracked by generations (worst case for recyclability). Parts are then made from each generation and tested for mechanical properties and accuracy.
- Compared to selective laser sintering (SLS) technology. Providing an elongation at break XY of 50% with 80% post-production surplus powder reusability according to the ASTM D638 test method. For testing, material is aged in real printing conditions and powder is tracked by generations (worst case for recyclability). Parts are then made from each generation and tested for mechanical properties and accuracy.
- Easier to process than standard HP 3D High Reusability PA12, providing proper fusing along with good spreadability and compatibility due to its small particle size.
- The following technical information obtained (November 2017) may change and is representative of averages or typical values of the testing date and should not be used for specification purposes. These values refer to a balanced print mode with FW BD6.1.
- Test results realized under the ASTM D638 with a test rate of 50 mm/min, specimens type V.
- Test results realized under ASTM D790 Procedure B at a test rate of 13.55 mm/min.
- Liters refers to the materials container size and not the actual materials volume. Materials are measured in kilograms.
- The HP powder and agents do not meet the criteria for classification as hazardous according to Regulation (EC) 1272/2008 as amended.
- Compared to manual print retrieval process used by other powder-based technologies. The term "cleaner" does not refer to any indoor air quality requirements and/or consider related air quality regulations or testing that may be applicable.
- Compared to PA 11 materials available as of June, 2017. HP Jet Fusion 3D printing solutions using HP 3D High Reusability PA 11 provide 70% post-production surplus powder reusability, producing functional parts batch after batch.

© Copyright 2017 HP Development Company, L.P.

Nothing herein should be construed as constituting an additional warranty. The only warranties for HP products and services are set forth in the express warranty statements accompanying such products and services and/or in a written agreement between you and HP for such HP products and services. HP believes that the information herein is correct as of the date of its publication, however, HP EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF HP IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION PROVIDED. HP shall not be liable for technical or editorial errors or omissions contained herein and the information herein is subject to change without notice. In no event shall HP be liable for damages or losses of any kind or nature that result from the use of or reliance upon this information. The HP Jet Fusion 3D Materials have not been designed, manufactured or tested by HP for compliance with legal requirements for 3D printed parts and their uses and recipients are responsible for making their own determination as to the suitability of HP Jet Fusion 3D Materials for their purposes and uses.

